

C  
O  
L  
O  
R  
  
B  
Y  
  
D  
E  
S  
I  
G  
N  
  
T  
E  
C  
H  
N  
I  
C  
A  
L  
  
D  
A  
T  
A

## 3.5 V.O.C. ENAMEL SYSTEM

**PRODUCT: Enamel Colors**

### **FEATURES:**

Easy to apply  
Fast dry  
Outstanding gloss  
Superior flow-out and leveling  
Excellent durability  
Excellent gloss & color retention  
Economical to use

### **SURFACE PREPARATION:**

- Wash surface of vehicle with soap and water to remove tree sap and road dirt
- Wipe vehicle with wax & grease remover.
- Sand area as necessary to remove any rust or corrosion
- For optimum performance, prime bare metal with US-600 Sealer primer
- Prime repaired areas with 2K urethane primer
- Block primed body work with 400 grit or finer wet or dry sandpaper
- Cleanse area to be painted with wax & grease remover
- Reseal vehicle using US-600 universal sealer
- Blow off and tack vehicle before painting

8 parts	Enamel color
1 part	MMH-92 LV HARDENER
2 parts	Exempt solvent

**Continue: 3.5  
VOC Enamel**

### **APPLICATION INSTRUCTIONS:**

#### **V.O.C. INFORMATION:**

Enamel color	V.O.C.: <569 gll (4.75 #/gal)
Less exempt solvent	V.O.C.: <569 gll (4.75 #/gal)
Mixed product	V.O.C.: <419 g/l (3.5 #/gal)

***This product may require several components and must be mixed properly to comply with V. O. C. regulations. This product is not recommended as part of a multi-coat system if the V. O. C. exceeds local, state or Federal regulations.***

#### **Solid & Metallic Colors:**

- Adjust HVLP air pressure to 30 psi at the gun

- Allow 10-15 minutes flash time between color coats
- Allow vehicle to dry overnight before exposing to weather or finessing

•**Dry Times @ 75°F:**

- Dust free:* 20 minutes
- Tack Free:* 4 hours
- Tape Free:* 16 hours
- Delivery:* overnight

For maximum paint performance, vehicle should be kept above 75°F. Temperatures below 60°F will severely retard dry times and cure of urethanes..

Clean equipment with a quality lacquer thinner .  
Do not leave catalyzed paint in the gun more than 8 hours.

**RECOATING PROCEDURES**

**Catalyzed:**

Enamel containing MMH-92 LV urethane hardener may be recoated after 4 hours at 75°F

**TECHNICAL DATA:**

Pot life	4 Hrs	Florida exposure	2 years
Theoretical dry film	480 sq. ft.@ 1 mil	Gloss	90%
Repair-ability	Excellent	Wt. Solids	varies by color
Mix ratio	8:1	Flash point	65 F.
RTS Viscosity	19-22 sec Zahn #2	Humidity	very good
Solvent resistance	very good	color retention	Excellent

**PRODUCT SAFETY INFORMATION:**

Consult Material Safety Data Sheet