

M
I
N
I
M
I
X
—
7
T
E
C
H
N
I
C
H
A
L
D
A
T
A

Color-base 2K Sealer

FEATURES:

- ❖ Fast dry
- ❖ Fills 320 D.A. sand scratches
- ❖ One coat hiding
- ❖ Economical to use
- ❖ Excellent inter-coat adhesion
- ❖ Good flow & leveling
- ❖ May be clear-coated
- ❖ Excellent undertone color matching

RECOMMENDED UNDERCOATS:

- ❖ O.E.M. enamel & lacquers.
- ❖ Refinish enamels.
- ❖ Self Etching primer
- ❖ Acrylic Lacquer primer
- ❖ Epoxy primer.
- ❖ 2K urethane primer

SURFACE PREPARATION:

Bare Metal:

- ❖ Wash surface with mild detergent and water
- ❖ Cleanse surface with wax & grease remover
- ❖ Sand area as necessary to remove any rust or corrosion from the metal surfaces
- ❖ Wipe surface with wax & grease remover to remove any remaining contaminants
- ❖ Prime area with one full wet coat of US-600 Universal sealer
- ❖ Allow 30 minutes dry time before applying Color-base sealer

Pre-painted Surfaces:

- ❖ Wash surface with mild detergent and water
- ❖ Cleanse surface with wax & grease remover
- ❖ Sand area as needed to remove old paint or any rust
- ❖ Featheredge work area using 320 grit D.A. paper or
- ❖ Apply one full wet coat of Color-base sealer
- ❖ Allow Color-base 30 minutes dry time before topcoat

M
I
N
I
M
I
X

7

T
E
C
H
N
I
C
H
A
L

D
A
T
A

MIXING DIRECTIONS:

8 parts Color-base sealer
1 part MMH-93 Hardener
10% Urethane reducer

V.O.C. Information:

Color-base VOC: < 535g/l (4.46 #/gal)
Less exempt solvent VOC: < 535g/l (4.46 #/gal)
Product VOC: < 535G/L (4.46 #GAL) mixed

This product may require several components and must be mixed properly to comply with VOC regulations. This product is not recommended as part of a multi-coat system if the VOC exceeds local, state or federal regulations.

APPLICATION:

- ❖ Adjust HVLP air pressure to 30 PSI @ the gun.
- ❖ Apply 1 full wet coat Color-base sealer
- ❖ Allow 30 Minutes flash before applying topcoat

If Color-base is not top-coated within 24 hours, vehicle must be recoated with a fresh coat of Color-base.

CLEAN-UP:

Clean equipment with a quality lacquer thinner. DO NOT leave catalyzed material in gun for more than 30 minutes.

TECHNICAL INFORMATION:

| | |
|------------------------|---------------------|
| Color | ALL |
| Pot life | 30 minutes @ 75F |
| Mix Ratio | 8:1:10% |
| Theoretical dry film | 464 sq. ft. @ 1 mil |
| Color holdout humidity | Excellent |
| Resistance salt spray | Excellent |
| Adhesion | Outstanding |
| Recommended film build | .7-1.0 mils |
| Flash point | 65F |
| Dry sand | 60 minutes |
| Spray viscosity | 24-26 sec. Zahn #2 |